NASM1312-3 29 August 1997

ADOPTION NOTICE

NASM1312-3, "Fastener Test Methods Method 3 Humidity" was adopted on 29 August 1997 for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: Commander, Naval Air Warfare Center Aircraft Division, Code 414100B120-3 Highway 547, Lakehurst, NJ 08733-5100. DoD activities may obtain copies of this standard from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094. The private sector and other Government agencies may purchase copies from the Aerospace Industries Association, 1250 Eye Street NW, Washington, DC 20005.

NASM1312-3 Should be used instead of MIL-STD-1312-3, which was cancelled on 29 August 1997.

Custodians: Army - AV Navy - AS Air Force - 11

Review Activities: Army - AV, AR Navy - AS, SH Air Force - 11 DLA - IS Preparing activity: Navy - AS (Project No. 53GP-0285-03)

NATIONAL AEROSPACE STANDARD COPYRIGHT 1997 AEROSPACE INDUSTRIES ASSOCIATION OF AMERICA, INC. ALL RIGHTS RESERVED

NASM1312-3 STANDARD PRACTICE

FASTENER TEST METHODS

METHOD 3

HUMIDITY



THE INITIAL RELEASE OF THIS DOCUMENT SUPERSEDES MIL-STD-1312-3

DESIGNATION FOR THIS TEST METHOD REMAINS MIL-STD-1312-3

LIST OF CURRENT SHEETS									
NO.	1	2	3	4	5	6	7		
REV.	NEW								

FSC 53GP

SHEET 1 OF 7

APPROVAL DATE AUGUST 1997

APPROVAL DATE AUGUST 1997 USE OF OR RELIANCE UPON THIS DOCUMENT OR ANY AEROSPACE STANDARD IS ENTIRELY VOLUNTARY AIA DOES NOT QUALIFY SUPPLIERS OR CERTIFY CONFORMANCE OF ITEMS PRODUCED UNDER AEROSPACE STANDARDS. AIA MAKES NO REPRESENTATION OR CLAIM RESPECTING (1) THE SUITABILITY OF ITEMS FOR ANY PARTICULAR APPLICATION OR (2) THE EXISTENCE OF OR APPLICABILITY THERETO OF PATENT OR TRADEMARK RIGHTS.

NATIONAL AEROSPACE STANDARD COPYRIGHT 1997 AEROSPACE INDUSTRIES ASSOCIATION OF AMERICA, INC.

ALL RIGHTS RESERVED

NASM1312-3

FOREWORD

This standard sets forth a standard test method to simulate a high humidity environment for testing and determining a fastener's resistance to humid conditions.

SHEET 2

APPROVAL DATE AUGUST 1997

1 ŀ

APPROVAL DATE AUGUST 1997 USE OF OR RELIANCE UPON THIS DOCUMENT OR ANY AEROSPACE STANDARD IS ENTIRELY VOLUNTARY AIA DOES NOT QUALIFY SUPPLIERS OR CERTIFY CONFORMANCE OF ITEMS PRODUCED UNDER AEROSPACE STANDARDS. AIA MAKES NO REPRESENTATION OR CLAIM RESPECTING (1) THE SUITABILITY OF ITEMS FOR ANY PARTICULAR APPLICATION OR (2) THE EXISTENCE OF OR APPLICABILITY THERETO OF PATENT OR TRADEMARK RIGHTS.

Copyright Aerospace Industries Association of America Inc. Provided by IHS under license with AIA/NAS No reproduction or networking permitted without license from IHS

Sold to:INFORMATION HANDLING SERVICES, 01874946 Not for Resale,2011/9/1 16:58:33 GMT

1

COPYRIGHT 1997 AEROSPACE INDUSTRIES ASSOCIATION OF AMERICA, INC. ALL RIGHTS RESERVED

LL RIGHTS RESERVED

NASM1312-3

TABLE OF CONTENTS

Sheet Paragraph 1 1.1 REFERENCED DOCUMENTS...... 4 2. 2.1 2.1.1 Specifications, Standards and Handbooks 4 3. 4 4.1 4.1.1 4.2 5 5.1 5.1.1 5.2 5.2.1 5.2.2 5.3 5.4 6. 6.1

SHEET 3

APPROVAL DATE AUGUST 1997

U

USE OF OR RELIANCE UPON THIS DOCUMENT OR ANY AEROSPACE STANDARD IS ENTIRELY VOLUNTARY AIA DOES NOT QUALIFY SUPPLIERS OR CERTIFY CONFORMANCE OF ITEMS PRODUCED UNDER AEROSPACE STANDARDS. AIA MAKES NO REPRESENTATION OR CLAIM RESPECTING (I) THE SUITABILITY OF ITEMS FOR ANY PARTICULAR APPLICATION OR (2) THE EXISTENCE OF OR APPLICABILITY THERETO OF PATENT OR TRADEMARK RIGHTS.

©COPYRIGHT 1997 AEROSPACE INDUSTRIES ASSOCIATION OF AMERICA. INC. ALL RIGHTS RESERVED

NASM1312-3

1. SCOPE

1.1 Applicability. This method covers a procedure for testing fasteners in a high humidity environment.

2. REFERENCED DOCUMENTS

2.1 Government documents.

2.1.1 <u>Specifications, standards and handbooks</u>. Unless otherwise specified, the following specifications, standards and handbooks of the issue listed in the current Department of Defense Index of Specifications and Standards (DoDISS) and the supplement thereto (if applicable), form a part of this standard to the extent specified herein.

STANDARDS

MILITARY

MIL-STD-889 Dissimilar Metals

(Copies of specifications, standards, handbooks, drawings and publications required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

3. DEFINITIONS Not applicable.

4. GENERAL REQUIREMENTS

4.1 <u>Test apparatus</u>. Test apparatus used in the humidity test shall include the following:

- a. Exposure chamber with racks for supporting the specimens.
- b. Water reservoir.

c. Means for creating and maintaining humidity within the required level.

d. Means for heating the exposure chamber and controlling its temperature.

e. Means for cleaning the air before humidifying it.

f. Indicative means for humidity level.

g. Indicative means for temperature.

SHEET 4

APPROVAL DATE AUGUST 1997

USE OF OR RELIANCE UPON THIS DOCUMENT OR ANY AEROSPACE STANDARD IS ENTIRELY VOLUNTARY AIA DOES NOT QUALIFY SUPPLIERS OR CERTIFY CONFORMANCE OF ITEMS PRODUCED UNDER AEROSPACE STANDARDS. AIA MAKES NO REPRESENTATION OR CLAIM RESPECTING (1) THE SUITABILITY OF ITEMS FOR ANY PARTICULAR APPLICATION OR (2) THE EXISTENCE OF OR APPLICABILITY THERETO OF PATENT OR TRADEMARK RIGHTS.

COPYRIGHT 1997 AEROSPACE INDUSTRIES ASSOCIATION OF AMERICA, INC.

ALL RIGHTS RESERVED

NASM1312-3

4.1.1 <u>Exposure chamber</u>. The chamber and all accessories shall be made of material such as glass, hard rubber, plastic, or suitably-coated wood that will not affect the corrosiveness of the humidity. In addition, all parts that come in contact with the test specimens shall be made of materials that will not cause galvanic or electrolytic corrosion. The chamber and accessories shall be constructed and arranged as follows:

- a. There shall be no dripping of the condensate on the specimens.
- b. The humidity atmosphere shall circulate freely about all specimens to the same degree.
- c. No condensate, which has come into contact with test specimens, shall return to the humidity cycle.
- d. The chamber shall be properly vented.

4.2 Test specimens.

1 . .

4.2.1 Specimens shall be given a minimum of handling and shall be prepared for test immediately before exposure. Specimens shall be handled with clean lintless gloves.

4.2.2 Specimens shall be racked or supported in such a manner that the atmosphere will not condense and gather in recesses or other features of the fastener and will circulate freely about all specimens to the same degree.

4.2.3 Specimens shall be cleaned with detergent and rinsed with deionized water to obtain a waterbreak-free surface, followed by rinsing with isopropyl alcohol and air or blow drying. No halogenated solvents or abrasives of any type are permitted. Cleaning must be done within one hour of test, shall be processed with a minimum of handling and shall be handled only with clean, lintless cotton gloves after the cleaning operation.

4.2.4 Unless specified in the product specification, dissimilar materials as defined in MIL-STD-889 must not be tested in the same cabinet at the same time.

5. DETAIL REQUIREMENTS

5.1 Test procedures.

5.1.1 <u>Location of specimens.</u> Whenever possible, a specimen shall be supported from the bottom or the side. When specimens are suspended from the top, suspension shall be by means of nylon cord or glass hooks. The use of metal hooks is not permitted. Specimens shall be so positioned that:

- a. They do not contact each other or any metallic material or any material capable of acting as a wick.
- b. They are not shielded from condensate from the atmosphere.

SHEET 5

APPROVAL DATE AUGUST 1997 USE OF OR RELIANCE UPON THIS DOCUMENT OR ANY AEROSPACE STANDARD IS ENTIRELY VOLUNTARY AIA DOES NOT QUALIFY SUPPLIERS OR CERTIFY CONFORMANCE OF ITEMS PRODUCED UNDER AEROSPACE STANDARDS. AIA MAKES NO REPRESENTATION OR CLAIM RESPECTING (1) THE SUITABILITY OF ITEMS FOR ANY PARTICULAR APPLICATION OR (2) THE EXISTENCE OF OR APPLICABILITY THERETO OF PATENT OR TRADEMARK RIGHTS.

COPYRIGHT 1997 AEROSPACE INDUSTRIES ASSOCIATION OF AMERICA, INC. ALL RIGHTS RESERVED

NASM1312-3

c. Corrosion products and condensate from one specimen does not fall upon another specimen or return to the humidifying reservoir.

5.2 Operating conditions.

.

5.2.1 <u>Temperature</u>. The test shall be conducted with the temperature in the exposure zone maintained at 120° F, +2° F, -3° F (49° C, +1° C, -1.7° C). Satisfactory methods for controlling the temperature accurately are by housing the apparatus in a properly controlled constant-temperature prior to humidifying, or by jacketing the apparatus and preheating the air to the proper temperature of water or of the air used in the jacket. No surface in the chamber shall become overheated enough to cause evaporation of condensate followed by condensation of that moisture on the other specimens. The use of immersion heaters within the chamber, for the purpose of maintaining the temperature within the exposure zone, is prohibited.

5.2.2 <u>Humidification</u>. Only distilled or deionized water shall be used in humidifying the chamber.

5.2.2.1 The conditions maintained in all parts of the exposure zone shall be 90 percent ± 5 percent relative humidity.

5.3 <u>Length of test</u>. Unless otherwise specified, the length of the humidity test shall be 96 hours. The test shall be run continuously until the time indicated or until definite indication of failure is observed, with interruptions only for adjustment of the apparatus and inspection of the specimen. Operations shall be so scheduled that interruptions are held to a minimum.

5.4 <u>Examination of specimens</u>. At the end of the test, the specimens shall be examined immediately to determine compliance with the standard of acceptability specified in the product specification or drawing.

6. NOTES

6.1 <u>Test report</u>. Unless otherwise prescribed in the product specification or drawing, for the material or product being tested, the test report shall contain the following data:

- a. Readings of humidity within the exposure zone of the chamber.
- b. Readings of temperature within the exposure zone of the chamber.
- c. Type of specimen and its dimensions, or part number, lot number, or description of part tested.
- d. Method of supporting specimens in the humidity chamber.
- e. Length of exposure period.
- f. Cause and length of interruptions during the test.

SHEET 6

APPROVAL DATE AUGUST 1997

USE OF OR RELIANCE UPON THIS DOCUMENT OR ANY AEROSPACE STANDARD IS ENTIRELY VOLUNTARY AIA DOES NOT QUALIFY SUPPLIERS OR CERTIFY CONFORMANCE OF ITEMS PRODUCED UNDER AEROSPACE STANDARDS. AIA MAKES NO REPRESENTATION OR CLAIM RESPECTING (1) THE SUITABILITY OF ITEMS FOR ANY PARTICULAR APPLICATION OR (2) THE EXISTENCE OF OR APPLICABILITY THERETO OF PATENT OR TRADEMARK RIGHTS.

NATIONAL AEROSPACE STANDARD ©COPYRIGHT 1997 AEROSPACE INDUSTRIES ASSOCIATION OF AMERICA, INC. ALL RIGHTS RESERVED

NASM1312-3

g. Results of all inspections.

1 . .

h. Method of specimen preparation such as cleaning.

i. Conclusions drawn from the test.

j. Instrumentation model number, serial number, and calibration date.

NOTE: For quality assurance testing, the report shall only specify:

a. The humidity test was conducted in accordance with Method 3.

b. The exposure time.

Į,

c. The results of final inspection.

SHEET 7

APPROVAL DATE AUGUST 1997 USE OF OR RELIANCE UPON THIS DOCUMENT OR ANY AEROSPACE STANDARD IS ENTIRELY VOLUNTARY AIA DOES NOT QUALIFY SUPPLIERS OR CERTIFY CONFORMANCE OF ITEMS PRODUCED UNDER AEROSPACE STANDARDS. AIA MAKES NO REPRESENTATION OR CLAIM RESPECTING (1) THE SUITABILITY OF ITEMS FOR ANY PARTICULAR APPLICATION OR (2) THE EXISTENCE OF OR APPLICABILITY THERETO OF PATENT OR TRADEMARK RIGHTS.